

Physi ViewCalc®

Operator Instructions

Microsoft Excel is a registered trademark of Microsoft Corporation.

Product Description

The Physi ViewCalc tool enables you to import, enter, or copy and paste an isotherm data set into Excel and use the following data reduction methods to manipulate data and produce plots and data overlays.

- BET surface area
- Langmuir surface area
- t-Plot

License

Before using this software, review the License for the terms of usage.

Isotherm Data and Overlay Isotherm Data

You may import, copy and paste, or manually enter data from one isotherm data set. The tool comes with a sample isotherm data file that contains results from a carbon reference material analysis. You may select a different isotherm data file at any time. Only one isotherm data file may be used at a time.

You may select up to five data sets to be overlaid on the isotherm data for each type of data reduction. The name of the overlaid file appears in the legend below the graph.

When you import an Overlay Isotherm Data File, the raw data are imported into a worksheet containing the following columns:

Column A: Absolute Pressure (mmHg)

Column B: Relative Pressure (p/p°)

Column C: Quantity Adsorbed (cm³/g STP)

Column D: Time - Hours since the beginning of the analysis at which the point was recorded

Column H: The name of the gas in the data file

Isotherm Menu

The Isotherm menu appears in the menu bar at the top of the screen in Excel 2003 and under the Add-ins tab in Excel 2007. The following commands are available from this menu:

- **Show Isotherm**
 - Show BET**
 - Show Langmuir**
 - Show t-Plot**

These commands enable you to view the associated worksheet.

- **Import Isotherm Data**

Enables you to select a different isotherm data file.

- **Import Overlay Isotherm Data**

Enables you to select one or more data files to be overlaid on the isotherm data file. When you import an overlay file, it is added to the Overlays list which appears when you choose the Add/Remove Overlays function.

- **Create Overlay Sheet**

Enables you to create a blank overlay sheet with the columns labeled as described previously.

- **Add/Remove Overlays**

You may select this function when a graph is displayed in the current worksheet. A dialog box displays that allows you to select up to five overlay files from drop-down lists. You may also remove an existing overlay file by double-clicking its name in the list.

- **Refresh**

Restores the data in tables to their original imported format.

- **Create Isotherm Chart**
- **Create BET Chart**
- **Create Langmuir Chart**
- **Create t-Plot Chart**

These commands enable you to recreate Isotherm, BET, Langmuir, or t-Plot graphs if they were removed.



Isotherm Data Worksheet

Isotherm Data Table

The Isotherm Data Table contains three columns: Absolute Pressure, Relative Pressure, and Quantity Adsorbed. The table contains both adsorption and desorption points. The last adsorption point in the table is highlighted in green.

Isotherm Data Graphs

Two graphs are shown on each worksheet: linear and logarithmic. Linear X-axes begin at zero; logarithmic X-axes begin at the selected data point. The name of the overlaid file is shown in the legend below the linear graph.



Methods of Adding Isotherm Data

You may add data to the Isotherm Data Table in one of several ways:


- You may import isotherm data. The data to be imported must be in one of the following formats.

Format	Description
ISO	This file format is used by some Micromeritics gas adsorption applications to export isotherm data. This is a CSV (comma separated value) file with the following columns of data: Absolute Pressure, Relative Pressure, Volume Adsorbed, and run time.
TXT	This file format contains some lines of header information, and then the isotherm data. On loading this file, you are prompted to select the data in columns A through D, the starting line of data, and the type of delimiters in the file. The defaults are setup to support the export format of Micromeritics gas adsorption software.

- You may copy data from a text file and paste it into the table.
- You may manually enter data into the table.

Importing Isotherm Data in ISO Format

1. Open the Isotherm Data worksheet.
2. Click **Isotherm > Import Isotherm Data** on the menu at the top of the screen.
3. The Open dialog displays. Select one or more ISO files, then click **Open**.
4. A dialog box enabling you to enter a gas is displayed.




5. Select a gas from the drop-down list. If you selected more than one file, you can click the **Apply to All Selected Files** box to apply the same gas to all data files.
6. Click the **Submit** button to apply the gas and close the dialog box.
7. The table and graphs are populated with data from the isotherm file and a worksheet containing the data in the isotherm file is added to the project.

Absolute Pressure (mmHg)	Relative Pressure (p/p°)	Quantity Adsorbed (cm ³ /g STP)
0.000951	0.00002608	5.1001
0.001944	0.00004902	10.2007
0.003654	0.00008642	15.3004
0.006442	0.00014509	20.3994
0.010816	0.00023315	25.4971
0.01738	0.00036034	30.5928
0.026862	0.00053843	35.6855
0.040139	0.00078369	40.7753
0.058423	0.00111531	45.8598
0.083145		50.9379

Importing Isotherm Data in TXT Format

1. Open the Isotherm Data worksheet.
2. Click **Isotherm > Import Isotherm Data** on the menu at the top of the screen.
3. The Open dialog displays. Select one or more TXT files, then click **Open**.
4. The Import Delimited Text File dialog box displays.



5. From the drop-down lists, select the data to be imported into Columns A through D (1st column through 4th column).
6. Select the first line of data to be imported into the data table.
7. Click the appropriate radio button for the type of delimiters used in the file.
8. Click **Submit**.

Copy and Pasting Data or Manually Entering Data

You can edit and enter data using the following methods:

- Delete data from the data table
- Copy and paste data from a text file into the data table
- Type data into the data table

Methods of Adding Overlays to an Isotherm

You may add overlays to isotherms in one of several ways:


- You may import overlay isotherm data. The data to be imported must be in ISO or TXT format.
- You may select an overlay data file from data files that already exist in the Excel project.
- You may create a new Overlay sheet and add data to it.

Importing Overlay Isotherm Data




These instructions refer to ISO formatted data. To import TXT data, refer to [“Importing Isotherm Data in TXT Format”](#) on page 6.

1. Open the Isotherm Data worksheet.
2. Click **Isotherm > Import Overlay Isotherm Data** on the menu at the top of the screen.
3. The Open dialog displays. Select one or more files, then click **Open**.
4. A dialog box enabling you to enter a gas is displayed.



5. Select a gas from the drop-down list. If you selected more than one file, you can click the **Apply to All Selected Files** box to apply the same gas to all data files.
6. Click the **Submit** button to apply the gas and close the dialog box.
7. Click the **Add/Remove** button at the top of the worksheet to display the Overlays dialog box.




8. Click an arrow to display a drop-down list of overlay data files. Select the desired files. (To remove a file, double-click its name in the list.)
9. Click **Close** to close the dialog box.
10. The data from the file are overlaid on the isotherm data in the graphs.

Selecting an Existing Overlay Data File

To select data from a file that is currently in the Excel project, follow Steps 8 through 11 on the previous page.

Creating a New Overlay Sheet

- Click **Isotherm > Create Overlay Sheet** on the menu at the top of the screen to display a new worksheet. Columns A through D are labeled as follows:
 - Column A:** Absolute Pressure (mmHg)
 - Column B:** Relative Pressure (p/p°)
 - Column C:** Quantity Adsorbed (cm³/g STP)
 - Column D:** Time - Hours since the beginning of the analysis at which the point was recorded. This data is not used in calculations, so this column can be left blank.



- You can import data, enter data, or copy and paste data into the worksheet.



The data you enter in the columns must be consistent with the column headings.



The program assumes that adsorption data are monotonically increasing and that desorption data are monotonically decreasing.

3. If you import a TXT file, the following dialog box displays.

- Select the data to be imported into Columns A through D (1st through 4th columns).
 - Select the first line of data you want to include in the data table.
 - Select the type of delimiters in the file.
 - Click **Submit**.
- If you manually entered or copied and pasted data into the columns, click the **Refresh ISO List** button.
 - The worksheet will now be added to the **Add/Remove Overlays** list.

Selecting a Different Gas

On the Isotherm Data worksheet:

- Click in the row below the **Update All Gas** button. An arrow appears. Click the arrow to display a list of gases.



Gases are added to the project on the Parameter Worksheet.

- Select the desired gas from the list. The gas is changed for the isotherm.
- If you wish to have the gas you selected apply to all reports, click the **Update All Gas** button.

Data Reduction Worksheets

Type of Data Reduction Worksheets

The Physi View Calc tool supports three methods of data reduction:

- The BET calculation obtains the sample surface area value by determining the monolayer volume of adsorbed gas from the isotherm data.
- The Langmuir calculation determines the surface area of a sample by relating the surface area to the volume of the gas adsorbed as a monolayer.
- The t-Plot calculation allows quantitative analysis of the area and total volume ascribed to micropores. Matrix area, the area external to micropores, is directly determined and often proves to be a valuable way of characterizing complex mixed materials.

Selecting Overlay Files

You may select up to five files to overlay on the primary data file. Refer [“Methods of Adding Overlays to an Isotherm” on page 6.](#)

Viewing Analysis Results and Parameters

Analysis raw results and parameters are shown above the data table.

Minimum/Maximum Analysis		min.	max
Fit Data Limits		0.015255688	0.103959526
Experimental Data Limits		0.005000000	0.500000000

BET Surface Area (m ² /g)	613.6214821	3.430340275 +-
C	-549.708738	
Qm (cm ³ /g STP)	140.9587517	
Slope (g/cm ³ STP)	0.007107179	0.000038 +-
Y-Intercept (g/cm ³ STP)	-0.000012906	9.85974E-06 +-
Correlation	0.999795567	
Molecular CSA (nm ²)	0.162	Nitrogen

Analysis results and parameters

BET Data		Isotherm Data Source: 13X_N2	
Relative Pressure (p/p ⁰)	Quantity Adsorbed (cm ³ /g STP)	1/[Q(p ⁰ /p-1)]	
0.008068979	149.0307	5.45835E-05	
0.011780373	150.5099	7.92028E-05	

You may change the gas as follows:

1. Click in the gas cell.
2. An arrow appears. Click the arrow to display a drop-down list of gases.
3. Click the desired gas.

When working with t-Plots, you may also select a different thickness curve.

Micropore Volume (cm³/g):	0.438425522	
Micropore Area (m²/g):	1101.7088	
External Surface Area (m²/g)	153.8131	
Molecular CSA (nm ²)	0.162	Nitrogen
Molecular DCF	0.0015468	
Surface Area Correction Factor	1	
Total Surface Area (m ² /g)	1255.521892	
Thickness Curve		Harkin-Jura
t-Plot Surface Area (m ² /g)	0.014837873	Halsey
Slope (cm ³ /g-A STP)	9.943956377	Harkin-Jura
Y-Intercept (cm ³ /g STP)	283.440342941	Broekoff-de Boer
Correlation	0.978485306	Carbon Black STSA
		User Defined

1. Click the Thickness Curve cell.
2. An arrow appears. Click the arrow to display a drop-down list of thickness curves.
3. Click the desired thickness curve.



Thickness curve parameters can be edited on the Parameter Worksheet.

Selecting Data Points

micromeritics® www.micromeritics.com		Add/Remove Overlays	
Minimum/Maximum Analysis	min.	max	
Fit Data Limits	0.015255688	0.103959526	
Experimental Data Limits	0.005000000	0.500000000	
BET Surface Area (m ² /g)	1255.521892	8.109721363 +/-	
C	2119.345366		
Qm (cm ³ /g STP)	288.4136292		
Slope (g/cm ³ STP)	0.003465607	0.000021 +/-	
Y-Intercept (g/cm ³ STP)	0.000001636	6.81149E-06 +/-	
Correlation	0.999848442		
Molecular CSA (nm ²)	0.162	Nitrogen	
BET Data		Isotherm Data Source: CARBSV-G	
Relative Pressure (p/p ⁰)	Quantity Adsorbed (cm ³ /g STP)	1/[Q(p ⁰ /p-1)] (g/cm ³ STP)	
0.00569561	250.9413	2.2827E-05	
0.006926744	255.7133	2.72769E-05	
0.008178705	259.8842	3.17301E-05	
0.009988278	264.8926	3.80873E-05	
0.015255688	275.5049	5.82314E-05	
0.020162657	282.4978	7.28415E-05	
0.025311861	288.1534	9.01228E-05	

You can select a range of data points to include in the report using the following methods:

- Use the up and down arrow keys located above the minimum and maximum relative pressure cells to select the desired data range.
- Edit the values in the **Fit Data Limits** and **Experimental Data Limits** cells.

All data points from the main isotherm adsorption branch between the Experimental Data Limits are shown in the table. The points between the Fit Data Limits are the ones used for the calculation. These points are shown in green in the table.

Parameters Worksheet

The Parameters worksheet enables you to add gases to the program, edit the parameters of thickness curves, and enter user-defined thickness parameters.

Adding a Gas

Name	Symbol	DCF	CSA
Argon	Ar	0.142	0.0012800
Nitrogen	N ₂	0.162	0.0015468
Carbon Dioxide	CO ₂	0.170	0.0018306
Krypton	Kr	0.210	0.0012743

1. Click in the cell below the last gas listed in the gas table.
2. Enter the name of the gas and its symbol, Density Conversion Factor (DCF), and Molecular Cross-Sectional Area (CSA nm²). The gas will now appear in the drop-down gas lists.

Editing a Thickness Parameter

You can edit the parameters for the following types of thickness curves:

Halsey

$$t = \left[\frac{0.540}{\ln(p/p^*)} \right]^{0.333}$$

Harkins-Jura

$$t = \left[\frac{13.9900}{0.0340 - \log(p/p^*)} \right]^{0.500}$$

Broekoff-de Boer

$$\log (p/p^*) = \frac{-16.1100}{t^2} + 0.1682 e^{-0.1137 t}$$

Carbon Black STSA

$$t = 2.9800 + 6.4500 (p/p^*) + 0.8800 (p/p^*)^2$$

To edit a parameter, click on the appropriate parameter and type the changes.

Thickness Curves			
Type:	Prm1	Prm2	Prm3
Halsey	3.54	-5	0.333
Harkin-Jura	13.99	0.034	0.5
Broekoff-de Boer	-16.11	0.1682	-0.1137
Carbon Black STSA	2.98	6.45	0.88
User Defined			

Adding a User-Defined Thickness Curve

In addition, you can enter data and parameters for a User Defined thickness curve. Enter the Relative Pressure and Thickness for each data point in the data table.

User Defined Thickness	
Relative Pressure (p/p ^o)	Thickness (A)
0.009988278	3.637999296
0.015255688	3.756744385
0.020162657	3.844061852
0.025311861	3.921671867
0.02965112	3.979543447
0.034921001	4.043142319
0.040036932	4.099539757
0.044959911	4.149963856
0.050010123	4.198503494
0.075176831	4.408065796
0.103959526	4.608951569
0.130074006	4.771754742